

Spectroscopic evidence for unconventional superconductivity in UBe_{13}

Ch. Wälti and H. R. Ott

Laboratorium für Festkörperphysik, ETH-Hönggerberg, 8093 Zürich, Switzerland

Z. Fisk

National High Magnetic Field Laboratory, Tallahassee, FL 32306-4005, USA

J. L. Smith

Los Alamos National Laboratory, Los Alamos, New Mexico 87545, USA

In a recent letter [1], we reported the observation of giant zero-bias conductance peaks (ZBCPs) for contacts between Au wires and bulk UBe_{13} , which we ascribed to the existence of low-energy Andreev surface bound-states in superconducting UBe_{13} . In the comment [2] preceding this reply, Gloos proposes an alternative interpretation of the ZBCPs observed in Ref. [1] which is based on Wexler's formula [2]. Below, we first show that the criticism of our interpretation by Gloos is not relevant for the experimental situation discussed in Ref. [1] and second, we argue that the observed ZBCPs in the UBe_{13} -Au contacts are not compatible with the interpretation given in Ref. [2].

In Ref. [2], Gloos discusses the properties of normal metal-normal metal (NN) contacts by means of Wexler's formula, from which he derives a condition claiming that the UBe_{13} -Au contacts discussed in Ref. [1] are not in the limit where pure Andreev reflection (AR) [4] may occur. Pure AR, or electron-hole reflection, at the interface between a normal conductor and a superconductor (NS) may cause an enhancement of the differential conductivity $G(E)$ for $|E| < \Delta$, where Δ denotes the amplitude of the superconducting energy gap, but only in the limit of a low potential-barrier at the interface [5]. The mean free path l in the contact, which is discussed in Ref. [2], is large, if the potential-barrier is small and vice versa. However, in our discussion of the observed ZBCPs we do not claim to observe an enhancement of the

differential conductivity of the contact due to pure AR. Instead we claim to observe a surface resonance phenomenon, which is caused by the presence of subgap Andreev bound-states. These two AR-type phenomena are simply not the same.

Wexler's formula, in the form used in Ref. [2], is, apart from other criteria, based on the assumption that the Fermi-liquid parameters and hence the resistivity ρ of both metals on either side of the contact are at least similar. Since in Ref. [1] one of the metals of the contact is the heavy-electron metal UBe₁₃, this assumption is certainly not valid, and Wexler's formula in the form as employed by Gloos [2] needs to be revised. In addition, the application of Wexler's formula for estimating the contact radius a using the contact resistance R and ρ of bulk UBe₁₃ is, in our opinion, an invalid step.

The interpretation of our experiments [1] which is proposed in Ref. [2] is based on the assumption that the loss of the electrical resistance of UBe₁₃ in its superconducting state is responsible for the huge enhancement of the differential conductivity at zero energy. The discussion given in Ref. [2] only embraces the temperature dependence of the conductivity of NN contacts. Discussing the *energy*-dependent differential conductivity $G(E)$ of, e.g., UBe₁₃-Au contacts, however, would require a model including its *energy* dependence. This important issue is not contained in the discussion presented in Ref. [2].

It is well known that superconductivity of UBe₁₃ with zero electrical resistance is fully established within a few ten mK below T_c . Therefore, in the context of Gloos' model, one would expect, for $|E| < \Delta$, the differential conductivity of the UBe₁₃-Au contact to increase sharply at T_c , reaching its maximum just below T_c . In that case there would be no obvious reason why the differential conductivity at zero energy, $G(0)$, should further increase substantially with decreasing temperature, as it is observed for the data discussed in Ref. [1].

The shape of the $G(E)$ curve of the UBe₁₃-Au contact (see Fig. 3 of Ref. [1]) does also not match the predictions of the model proposed by Gloos. The electrical resistance of UBe₁₃ at $T < T_c$ is zero for $|E| < \Delta$. The model discussed in Ref. [2] does not offer an explanation, why $G(E)$ of the UBe₁₃-Au contact is only strongly enhanced in a narrow region around zero

bias, but substantially *reduced* compared to the normal state of the contact at intermediate energies $|E| < \Delta$.

We acknowledge helpful discussions with M. Sigrist.

REFERENCES

- [1] Ch. Wälti, H. R. Ott, Z. Fisk, and J. L. Smith, Phys. Rev. Lett. **84**, 5676 (2000).
- [2] K. Gloos, preceding Comment, Phys. Rev. Lett. (2000).
- [3] H. R. Ott, H. Rudigier, Z. Fisk, and J. L. Smith, Phys. Rev. Lett. **50**, 1595 (1983).
- [4] A. E. Andreev, Zh. Eksp. Teor. Fiz. **46**, 1823 (1964) [Sovj. Phys. JETP **19**,1228 (1964)].
- [5] G. E. Blonder, M. Tinkham, and T. M. Klapwijk, Phys. Rev. B **25**, 4515 (1982).